



**TCC-5000A/5060B
(60 Shore A)
POLYURETHANE CASTING
SYSTEM**

PRODUCT BULLETIN



TOOL CHEMICAL COMPOSITES

**www.axson-technologies.com
31200 Stephenson Hwy**

**800.344.7776
Madison Heights, MI 48071**

**axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909**

DESCRIPTION

TCC-5000A/5060B is a two-component urethane casting system designed to give a 60 Shore A hardness material with exceptional toughness. This casting system offers outstanding performance properties including high strength, low shrinkage and easy processing. Ultimate properties are reached after 7 days at room temperature or by being cured for 16-20 hours at room temperature, then post cured for a minimum of 6 hours at 160°F (71°C).

Typical Applications Include: Long Lasting Flexible Molds • Industrial Wheels • Belts • Pulleys • Casters • Nesting Fixtures • Static Welding Fixtures • Metal Forming Pads • Sound Dampening Pads

TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)

Mix Ratio (parts by weight)	Resin TCC-5000A/Hardener TCC-5060B.....	100A/55B
Pot Life (150 gram mass)		15 - 20 minutes
Initial Mixed Viscosity		1,000 cps
Mixed Color		Amber
Shelf Life Resin/Hardener (in original unopened containers)		2 years

TYPICAL PHYSICAL PROPERTIES

Hardness Buildup (150 gram mass @ 77°F (25°C))	after 24 hours	45 - 50 Shore A
	after 48 hours	53 - 58 Shore A
	after 72 hours	60 - 65 Shore A
Cured Specific Gravity.....		1.09 g/cc
Tensile Strength		1,500psi (10MPa)
Elongation		600%
Linear Shrinkage		<0.001 in/in
Tear Strength, split		70 pli
Tear Strength, Die "C" Graves.....		200 pli

MIXING PROCEDURE

Use an accurate gram scale to properly weigh and proportion A/B components into a straight sided metal or plastic container for mixing. Paper or wax lined mixing containers can contain moisture and contaminate material. Next, use a metal or plastic mixing spatula to gently but thoroughly blend resin and hardener together. Once the urethane appears to be well mixed, pour into a second container and continue to mix for another two to three minutes. This procedure eliminates the possibility of any unmixed material being poured into the final cast. Vacuum degass mixture before casting to produce an air free part.

Continued on next page

MOLDS

Use TCC Casting Urethane systems for mold construction. You can choose from the TCC-5000 series of flexible Shore 'A' 50-95 systems or TCC-6000 series of semi-rigid Shore 'D' 60-75 systems. Urethane molds should be fully cured before use and require the application of mold release agent such as MR #10 high gloss mold release. MR #10 is a low viscosity, water clear, non-transferable polymer mold release that can be applied by brush or non-aerosol sprayer. Other mold release systems are available.

TCC CASTING URETHANES	
Flexible Tooling Elastomers	
TCC-5000A/5050B - 50 Shore A	TCC-5000A/5060B - 60 Shore A
TCC-5000A/5070B - 70 Shore A	TCC-5000A/5080B - 80 Shore A
TCC-5000A/5081B - 80 Shore A - long working life	
TCC-5000A/5090B - 90 Shore A	TCC-5000A/5095B - 95 Shore A
Rigid Tooling Elastomers	
TCC-6000A/6061B - 60 Shore D	TCC-6000A/6065B - 65 Shore D
TCC-6060A/B - 60 Shore D - short working life	
TCC-6000A/6070B - 70 Shore D	TCC-6075A/6075B - 75 Shore D
Pronto Parts for Rapid Prototyping	
TCC-8020A/TCC-8021B - 75 Shore D	TCC-8040A/B - 80 Shore D - High Temp
Crystal Clear Casting System	
TCC-6080 A/B - 80 Shore D	

SANITARY PRECAUTIONS

Do not take internally. Avoid prolonged breathing of vapors. Work in a well ventilated area. Avoid skin contact. Protective gloves should be worn. If contact occurs: wash skin with soap and water. Avoid eye contact. If contact occurs: rinse well with water for 15 minutes, contact physician.

STORAGE AND HANDLING

Store closed containers at 65°F-85°F (18°C-29°C). Partially used containers must be flushed with dry nitrogen and resealed. Materials are sensitive to moisture contamination.

TCC-5000A/5060B Tech/Revised 1/30/15
Supersedes 6/23/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it	JAPAN +81 5 64 26 25 91 sales.japan@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	MIDDLE EAST +971 7 2432227 axsonmideast@axson.com	SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	SPAIN +34 9 32 25 16 20 spain@axson.com	U.K. +44 16 38 66 00 62 sales.uk@axson.com	