



BUILDING TRUST



# EPOLAM 2092

Technical Data Sheet  
HIGH TEMP EPOXY LAMINATING / INFUSION SYSTEM  
416°F (213°C) Tg (TMA) – 553 cps. mixed viscosity

## DESCRIPTION

Production of composite tooling and structures by the usual impregnation methods (infusion, wet-lay-up).

## APPLICATIONS

- High performance, high temperature composite tools or parts for aerospace and other industries
- Suitable for infusion processing along with wet-layup and vacuum bagging processes

## PROPERTIES

- Very High Tg
- Low mixed viscosity
- Very Long pot life and working time
- R.T. set up 16 hrs ( brittle state)
- Self-supporting with only 16 hr/130°F cure
- Excellent ultimate properties after final post-cure

PHYSICAL PROPERTIES				
Composition	Units	2092 Resin	2092 Hardener	Mixed
Mix ratio – by weight		100	50	100/50
Mix ratio – by volume		100	63	100/63
Aspect		Liquid	Liquid	Liquid
Color	Visual	Lt. Amber	Colorless	Clear-Lt. Amber
Viscosity (25°C)	Cps	1,300	100	553
Specific Gravity (25°C)	lbs./gal (g/cc)	9.92 (1.19)	7.92 (.95)	9.48 (1.14) Cured
Gel Time (180 g) at 77°F (25°C)	minutes			730

## PROCESSING CONDITIONS

After mixing according to the indicated ratio, carry out impregnation of the reinforcements.  
To ensure an optimal use and a good impregnation, please use packaging stored at a temperature above 15 ° C.  
Do not leave large masses of material (more than 1" thickness in mixing cup) to cure at room temperature or above to prevent an exotherm and possible smoke generation of the material.

## CURE CONDITIONS

In order to avoid any risk of distortion or tooling shrinkage a precise curing cycle must be observed.  
Demolding takes place only after a 16 hour pre-curing at 50°C-60°C. Then the following thermal treatment (Post-cure) can be carried out : 2 hours at 120°C, 3 hours at 180°C (3 hours at 150°C optional – see property tables ) with an increase and a decrease in temperature of 20°C per hour between stages.

<b>SikaAxson US</b> +1 248 588 2270 axsonmh@axson.com sikaaxson.us	<b>CHINA</b> +86 21 58 68 30 37 marketing.china@axson.com <b>MEXICO</b> +52 55 52 64 49 22 marketing@axson.com.mx	<b>FRANCE</b> +33 1 34 40 34 60 axson@axson.com <b>SLOVAKIA</b> +42 1 76 42 25 26 axson.sk@axson.com	<b>INDIA</b> +91 20 25 56 07 10-11 info.india@axson.com <b>SPAIN</b> +34 9 32 25 16 20 spain@axson.com	<b>ITALY</b> +39 02 96 70 23 36 axson@axson.it <b>U.K.</b> +44 16 38 66 00 62 sales.uk@axson.com	<b>JAPAN</b> +81 5 64 26 25 91 sales.japan@axson.com	<b>SIKA GERMANY – SikaAxson</b> +49 7125 940 492 tooling@de.sika.com www.sikaaxson.de
---	--	---	---	---	--	--



BUILDING TRUST



# EPOLAM 2092

Technical Data Sheet  
 HIGH TEMP EPOXY LAMINATING / INFUSION SYSTEM  
 416°F (213°C) T<sub>g</sub> (TMA) – 553 cps. mixed viscosity

## Neat Cured Properties Tested at 74°F (23°C)

	Test Method	Unit(s)	Test Results
Glass Transition Temperature (T <sub>g</sub> ) *Cure #1 **Cure #2	ASTM E1545	°F (°C)	346 (174) 416 (213)
Hardness *Cure #1 **Cure #2	ASTM D-2240	Shore D	88 92
Flexural Strength *Cure #1 **Cure #2	ASTM D790	psi (MPa)	11,203 (77) 9,059 (63)
Flexural Modulus *Cure #1 **Cure #2	ASTM D790	psi (MPa)	420,904 (2904) 467,510 (3226)
Tensile Strength *Cure #1 **Cure #2	ASTM D638	psi (MPa)	5,287 (37) 3,572 (25)
Tensile Modulus *Cure #1 **Cure #2	ASTM D638	psi (MPa)	275,690 (1,902) 292,640 (2,019)
Tensile Elongation *Cure #1 **Cure #2	ASTM-D638	%	2.2 1.3

\*12hr/40°C + 2hr/120°C + 3hr/150°C cure

\*\*12hr/40°C + 2hr/120°C + 3hr/180°C cure

## Composite Cured Properties Tested at 74°F (23°C)

	Test Method	Unit(s)	Test Results
Flexural Strength *Cure #1 **Cure #2	ASTM D790	psi (MPa)	67,021 (462) 71,476 (493)
Flexural Modulus *Cure #1 **Cure #2	ASTM D790	psi (MPa)	5.04 M (34,776) 5.46 M (37,674)
Tensile Strength *Cure #1 **Cure #2	ASTM D638	psi (MPa)	57,525 (397) 62,710 (433)
Tensile Modulus *Cure #1 **Cure #2	ASTM D638	psi (MPa)	1.65 M (11,385) 1.52 M (10,488)
Tensile Elongation *Cure #1 **Cure #2	ASTM D638	%	4.0 4.3

Infused laminate - Carbon fiber, 3K plain weave, 8 layer, 0-90° rotation, 40% resin content

\*12hr/40°C + 2hr/120°C + 3hr/150°C cure \*\* 12hr/40°C + 2hr/120°C + 3hr/180°C cure

Page 2/3- July 5, 2018 US Rev 5

SikaAxson US  
+1 248 588 2270  
axsonmh@axson.com  
sikaaxson.us

CHINA  
+86 21 58 68 30 37  
marketing.china@axson.com  
MEXICO  
+52 55 52 64 49 22  
marketing@axson.com.mx

FRANCE  
+33 1 34 40 34 60  
axson@axson.com  
SLOVAKIA  
+42 1 76 42 25 26  
axson.sk@axson.com

INDIA  
+91 20 25 56 07 10-11  
info.india@axson.com  
SPAIN  
+34 9 32 25 16 20  
spain@axson.com

ITALY  
+39 02 96 70 23 36  
axson@axson.it  
U.K.  
+44 16 38 66 00 62  
sales.uk@axson.com

JAPAN  
+81 5 64 26 25 91  
sales.japan@axson.com

SIKA GERMANY –  
SikaAxson  
+49 7125 940 492  
tooling@de.sika.com  
www.sikaaxson.de



BUILDING TRUST



# EPOLAM 2092

## Technical Data Sheet

### HIGH TEMP EPOXY LAMINATING / INFUSION SYSTEM

416°F (213°C) Tg (TMA) – 553 cps. mixed viscosity

## STORAGE CONDITIONS

This product has a shelf life of 6 months for the resin as indicated by the expiration date on the container when stored in original unopened containers between 47°F – 77°F (8°C – 25°C), 9 months if stored below 47°F (8°C) and 12 months if stored below 0°F (-18°C). The product shelf life for the hardener is 24 months between 60°F (15°C) and 77°F (25°C). Any opened can must be tightly closed. It is recommended that opened containers be stored under an inert and/or dry gas cover (ex : dry air, Nitrogen).

## HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- Ensure good ventilation
- Wear gloves, and safety glasses

For additional information, please consult the Safety Data Sheet (SDS).

## DISCLAIMER

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the SikaAxson's products, under their own conditions, before commencing with the proposed application. In no event shall SikaAxson US be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

<p><b>SikaAxson US</b> +1 248 588 2270 axsonmh@axson.com sikaaxson.us</p>	<p><b>CHINA</b> +86 21 58 68 30 37 marketing.china@axson.com</p> <p><b>MEXICO</b> +52 55 52 64 49 22 marketing@axson.com.mx</p>	<p><b>FRANCE</b> +33 1 34 40 34 60 axson@axson.com</p> <p><b>SLOVAKIA</b> +42 1 76 42 25 26 axson.sk@axson.com</p>	<p><b>INDIA</b> +91 20 25 56 07 10-11 info.india@axson.com</p> <p><b>SPAIN</b> +34 9 32 25 16 20 spain@axson.com</p>	<p><b>ITALY</b> +39 02 96 70 23 36 axson@axson.it</p> <p><b>U.K.</b> +44 16 38 66 00 62 sales.uk@axson.com</p>	<p><b>JAPAN</b> +81 5 64 26 25 91 sales.japan@axson.com</p>	<p><b>SIKA GERMANY – SikaAxson</b> +49 7125 940 492 tooling@de.sika.com www.sikaaxson.de</p>
---	---	--	--	--	---	--