

### PROPERTIES

- Low density.
- Low hardness
- Time before machining shorter than 24 hours
- Good thermal resistance

PHYSICAL PROPERTIES				
Composition		RESIN	HARDENER	MIXING
Mix ratio by weight		100	100	
Aspect		viscous paste	viscous paste	viscous paste
Colour		grey	white	grey
Viscosity at 25 °C 0,9 s <sup>-1</sup> (Pa.s)	RM 100 Lamy	650	700	600
Specific gravity at 25 °C (g/cm <sup>3</sup> )	ISO 1675 : 1985	0.52	0.52	-
Specific gravity of cured product at 23 °C	ISO 2781 : 1996	-	-	0.55

THERMAL AND MECHANICAL PROPERTIES (1)			
Hardness	ISO 868 : 2003	Shore D1	51
Glass transition temperature (Tg)	ISO 11359 : 1999	°C	65
Coefficient of thermal expansion (CTE)	ISO 11359 : 1999	10 <sup>-6</sup> .K <sup>-1</sup>	88
Tensile modulus	ISO 527 : 1993	MPa	420
Tensile strength	ISO 527 : 1993	MPa	6
Elongation at break	ISO 527 : 1993	%	3.0
Flexural modulus	ISO 178 : 2001	MPa	500
Flexural strength	ISO 178 : 2001	MPa	10
Compressive strength at yield stress	ISO 604 : 2002	MPa	7.3

(1) : Average values obtained on standard specimens / Hardening 24 hr at 23 °C + 16 hr at 40 °C

**During processing the dispensing nozzle must be maintained perpendicular to the surface on which the product is applied. Ensure overlap of ribbon.**

**CAUTION : Exotherm mostly depends of the type of machine and of the working parameters such as :**

- Room temperature.
- Insulating property of support.
- The mixture temperature (depending of the type of mixer: static or dynamic) and the speed of mixing and output.
- Applied thickness.

TDS15F0045- 2015,October 16th

### EXOTHERMIC PEAK AND HARDENING TIME \*

Thickness (mm)	Product temperature (°C)	Exothermic peak (min)	Exothermic peak (°C)	Workability (hours)
25	23	160	70	16 - 18

\* Room temperature : 23 °C ; polystyrene support.

### PROCESSING CONDITIONS

On vertical support, apply a thin coat of product with a spatula. This operation helps to reinforce the bonding on the support.

On ceiling application, apply a maximal thickness of 30 mm.

Use a dynamic mixer preferably.

Otherwise, double length of static mixer.

For dynamic mixing machine ,please contact us for parameters : [composite@axson.fr](mailto:composite@axson.fr)

### HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- ensure good ventilation,
- Wear gloves, safety glasses and protective clothes.

For further information, please consult the product safety data sheet.

### STORAGE CONDITIONS

Use within 9 months of the manufacturing date. Expiry date indicated on the packaging.

### GUARANTEE

The information of our technical data sheet is based on our present knowledge and the result of tests conducted under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON refuse any guarantee about the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The guarantee conditions are regulated by our general sale conditions.

TDS15F0045- 2015,October 16th