



BUILDING TRUST



F160 ISOCYANATE F160-1 POLYOL

FASTCAST POLYURETHANE RESIN
CAN BE FILLED
POT-LIFE 2'20 – Tg 110°C

APPLICATIONS

Negatives, molds, masters and mock-ups using the unfilled product or filled with RZ 30150 mineral filler in order to avoid an exothermic reaction and to get easy machining.

Thermoforming masters using the product filled with RZ 209/6 aluminium powder in order to increase thermal conductivity.

PROPERTIES

- Quick setting system
- Low viscosity
- Good temperature resistance after heat curing
- Phthalate free
- Easy-to-use mix ratio (1:1 by weight)
- Adjustable filler content
- REACH and ROHS compliant

PHYSICAL PROPERTIES

Composition		POLYOL	ISOCYANATE	UNFILLED MIXTURE	MIXTURE FILLED RZ 30150
Mixing ratio by weight		100	100	-	360
Aspect		Liquid	Liquid	Liquid	Liquid
Color		Off-white	Amber	Beige	Beige
Viscosity at 25°C (mPa.s)	BROOKFIELD LVT	110	60	90	3000
Density of liquid parts	ISO 1675	0.97	1.1	1.08	1.67
Density of cured mixing at 23°C	ISO 2781	-	-		
Pot life at 25°C on 200g (min)	Gel Timer TECAM			2'20	3'30

MECHANICAL PROPERTIES AT 23°C (1)

Hardness	ISO 868	Shore D1	75
Flexural modulus	ISO 178	MPa	1300
Flexural strength	ISO 178	MPa	60
Charpy impact resistance <i>Unnotched test samples</i>	ISO 179/1eU	kJ/m ²	14

THERMAL AND SPECIFIC PROPERTIES (1)

Glass transition temperature (Tg)	ISO 11359-2	°C	110
Demolding time at 25°C: thickness of 10 mm	Internal method	min	30

(1): Average values obtained on standardized specimens / Hardening 16 hours at 70°C



BUILDING TRUST



F160 ISOCYANATE

F160-1 POLYOL

FASTCAST POLYURETHANE RESIN

CAN BE FILLED

POT-LIFE 2'20 – Tg 110°C

PROCESSING CONDITIONS

Before use, the polyol must be mixed until both color and aspect become homogeneous. The polyol and the Isocyanate must be mixed at a temperature equal or above 18°C according to the mix ratio indicated on this technical data sheet.

For casting thicknesses above 5 mm and up to 40 mm, it is recommended to add filler as follows:

- up to 360 phr of RZ 30150 filler (mineral filler)
- up to 360 phr of RZ 209/6 filler (aluminium powder)

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation,
- Wear gloves and safety glasses.

For further information, please consult the product safety data sheet.

STORAGE CONDITIONS

Shelf life of both parts is 12 months, in a dry place and in their original unopened containers at a temperature between 15 to 25°C. Any open must be tightly closed under dry inert gas (dry air, nitrogen, etc.).

PACKAGING

F160-1 POLYOL	F160 ISOCYANATE	KIT
6 x 0.9 Kg 1 x 4.5 kg 1x 18 Kg	6 x 0.9 Kg 1 x 4.5 Kg 1x 18 Kg	6 x (0.9+0.9) Kg 1 x (4.5+4.5) Kg 1 x (18+18) Kg

GUARANTEE

Information of our technical data sheet is based on our present knowledge and the result of tests conducted under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products for his application under his own conditions. AXSON refuses any guarantee about the compatibility of a product with any particular application. AXSON disclaims all responsibility for damage from any incident which results from the use of these products. The guarantee conditions are regulated by our general sale conditions.

AXSON FRANCE - SikaAxson Head Office France +33 1 34 40 34 60 axson@axson.com www.sikaaxson.com	GERMANY +49 (0)7125 940 492 tooling@de.sika.com www.sikaaxson.de	SPAIN & PORTUGAL +34 93 225 16 20 spain@axson.com axson.es	SLOVAKIA +421 37 642 25 26 axson.sk@axson.com axson-ce.sk	USA +1 248 588 2270 axsonmh@axson.com axson-na.com	JAPAN +81 564 26 25 91 sales.japan@axson.com axson.jp	INDIA +91 20 25560710 info.india@axson.com axson.com
	ITALY +39 02 96 70 23 36 axson@axson.it axson.it	U.K. +44 1 638 66 00 62 sales.uk@axson.com axson.com	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx axson.com.mx	CHINA +86 21 58 68 30 37 marketing.china@axson.com axson.cn		