

## APPLICATIONS

Used by casting in silicone molds for prototype parts and mock-ups whose mechanical properties are close to those of thermoplastics.

## PROPERTIES

- Low viscosity
- Long pot-life
- Good mechanical properties
- Can be painted
- Thermoplastic aspect

PHYSICAL PROPERTIES				
		PART A	PART B	MIXING
Composition		ISOCYANATE	POLYOL	
Mixing ratio by weight		100	100	
Aspect		liquid	liquid	liquid
Color		light to dark amber	Clear colorless	Off-white
Viscosity at 77°F (25°C) (mPa.s)	BROOKFIELD LVT	60	175	100
Specific gravity at 77°F (25°C)	ISO 1675 :1975	1.15	1.02	-
Specific gravity at 73° (23°C)	ISO 2781 :1988	-	-	1.06
Gel time at 77°F (25°C) on 200g (min.)	-			15 - 20

## PROCESSING

Mix polyol prior to weighing if it has been standing for more than a day.

Weigh according to the indicated ratio. Mix until a homogeneous and transparent mixing is obtained.

Degas for 5 minutes.

Cast in a silicone mold at room temperature or pre-heated at 95°F (35°C) – 104°F (40°C) to accelerate the process.

Demolding time and temp before post cure: Recommended 2 hours at 158°F (70°C) for parts with thickness less than an 1/8"

\* Demolding time dependent upon part geometry as well as temperature of liquid components and mold temperature.

After demolding cure 2 hours at 158°F (70°C) in order to obtain the optimal properties.

## PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- . ensure good ventilation
- . wear gloves and safety glasses

For further information, please consult the safety data sheet.

## MECHANICAL PROPERTIES AT 73°F (23°C) AFTER POSTCURE <sup>(1)</sup>

Cured color	Visual		Bright white
Tensile strength	ASTM D638	Psi/(MPa)	6,000/(41)
Tensile modulus		Psi/(MPa)	100,000/(690)
Elongation		%	8
Flexural strength	ASTM D790	Psi/(MPa)	7,000/(48)
Flexural modulus		Psi/(MPa)	200,000/(1,380)
Compressive strength	ASTM D695	Psi/(MPa)	7,000/(48)
Compressive modulus		Psi/(MPa)	175,000/(1,210)
Impact resistance, notched	ASTM D-256-05	ft.Lb.f/in <sup>2</sup> /(kJ/m <sup>2</sup> )	2.9/(6)
Hardness - at 73°F (23°C)	ASTM D-2240	Shore D1	74

## THERMAL & SPECIFIC PROPERTIES

Glass temperature transition <sup>(1)</sup>	TMA METTLER	°F (°C)	167 (75)
Coefficient of thermal expansion		10 <sup>-6</sup> °F <sup>-1</sup> /(10 <sup>-6</sup> °C <sup>-1</sup> )	56/(100)
Linear shrinkage <sup>(1)</sup>	-	%	0.1
Maximal casting thickness	-	In./(mm)	0.2/(5)
Demolding time @ 73°F (23°C)	-	Hours	4
Complete hardening time @ 73°F (23°C)	-	days	4

<sup>(1)</sup> Average values obtained on standard specimens/Postcure 12 hr at 158°F (70°C)

## STORAGE

*Shelf life is 6 months for PART A (Isocyanate) and 12 months for PART B (Polyol) in a dry place and in original unopened containers at a temperature between 60°F (15°C) and 77°F (25°C). Any open container must be tightly closed under dry nitrogen blanket.*

## GUARANTEE

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.