

Biresin® CR144 / CH141 / CA141 Composite resin system for heat curing

Areas of Application

- In particular for pultrusion and filament winding processing
- Specially for applications when low reactivity and a long potlife are required

Product Benefits

- Fast infiltration of dry fibres due to low mixed viscosity and an elevated processing temperature
- Adjustment of the potlife via the accelerator component

Description

- Basis Three-component-epoxy-system
- Resin (A) **Biresin® CR144**, epoxy resin, translucent
- Hardener (B) **Biresin® CH141**, carboxylic acid anhydride, transparent
- Accelerator (C) **Biresin® CA141**, amber

Physical Data	Resin (A)	Hardener (B)	Accelerator (C)
Individual Components	Biresin® CR144	Biresin® CH141	Biresin® CA141
Viscosity, 25°C	mPas	12.000	< 10
Density, 25°C	g/ml	1.16	1.20
Mixing ratio	in parts by weight	100	90
			Mixture
Potlife, 100 g / RT, approx. values	h		12
Mixed viscosity, 25°C, approx. values	mPas		800

Mechanical Data, neat resin specimen

approx. values after 3 h / 80°C + 8 h / 140°C (source: Sika internal)

Biresin® CR144 resin (A)		with Biresin® CH141 hardener (B) and Biresin® CA141 accelerator (C)	
Density	ISO 1183	g/cm³	1,20
Shore hardness	ISO 868	-	D 87
Flexural E-Modulus	ISO 178	MPa	3,000
Tensile E-Modulus	ISO 527	MPa	3,000
Flexural strength	ISO 178	MPa	140
Compressive strength	ISO 604	MPa	125
Tensile strength	ISO 527	MPa	80
Elongation at break	ISO 527	%	3.5
Impact resistance	ISO 179	kJ/m²	15

Processing

- Before demoulding an appropriate precuring is necessary.
- To clean brushes or tools immediately Sika Reinigungsmittel 5 is recommended.

Thermal data of neat resin specimen at different post curing conditions

Biresin® CR144 resin (A) with Biresin® CH141 hardener (B) and Biresin® CA141 accelerator (C)		
Glass Transition Temperature	ISO 11357 °C	155*
Heat Distortion Temperature	ISO 75B °C	147*
	ISO 75C °C	130*

* values after post curing: 3 h / 80°C + 8 h / 140°C

Packaging (net weight, kg)

Biresin® CR141 resin (A)	1,000	220	10
Biresin® CH141 hardener (B)	1,100	220	9
Biresin® CA141 accelerator (C)			0.2

Storage

- Minimum shelf life of Biresin® CR144 resin (A) is 24 month and of Biresin® CH141 hardener (B) and CA141 accelerator (C) is 12 month under room conditions (18 - 25°C), when stored in original unopened containers.
- After prolonged storage at low temperature, crystallisation of resin may occur. This is easily removed by warming up for a sufficient time to a maximum of 60-80°C.
- Containers must be closed tightly immediately after use. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: tooling@de.sika.com

Internet: www.sika.com

