



**TCC-205
LAMINATING &
ADHESIVE SYSTEM
ROOM TEMPERATURE**

PRODUCT BULLETIN



www.axson-technologies.com 800.344.7776 axsonmh@axson.com
31200 Stephenson Hwy Madison Heights, MI 48071 Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

Epoxy Resin **TCC-205** with either Epoxy Hardener **TCC-102** or **TCC-104** is a rigid epoxy system having low viscosity and a short pot life. This system is easy to use and has no objectionable fumes. Applications include as an adhesive system for the MP-1065 Model Plank®, MP-1055 Model Plank®, FP-1050 Fixture Plank® and the DP-1051 Die Plank®, and as an adhesive for adhering plastic to wood. This system is also well suited as an unfilled room temperature laminating resin, which provides excellent wet-out when using fiberglass and graphite cloth.

TYPICAL HANDLING CHARACTERISTICS AND PHYSICAL PROPERTIES @ 77°F (25°C)

Mix Ratio (by weight).....	Resin TCC-205	100 parts
.....	Hardener TCC-102.....	25 parts
.....	Hardener TCC-104.....	25 parts
Shelf Life (in original unopened containers)	TCC-205/TCC-102/104	2 years

	<u>TCC-102</u>	<u>TCC-104</u>
Pot Life (100 gram mass)	15 - 20 minutes	30 - 35 minutes
(1 pound mass).....	8 - 10 minutes	12 - 14 minutes
Specific Gravity (mixed).....	1.09 g/cc	1.10 g/cc
Mixed Viscosity.....	700 cps	800 cps
Cured Color	Clear Amber.....	Clear Amber
Peak Operating Temperature	180°F (82°C).....	180°F (82°C)
Hardness.....	82 - 85 Shore D.....	82 - 85 Shore D
Elongation (rigid)	2%.....	2%
Compressive Strength.....	30,000psi (207MPa).....	30,000psi (207MPa)
Tensile Strength	9,500psi (66MPa).....	9,500psi (66MPa)
Flexural Strength	18,000psi (124MPa).....	18,000psi (124MPa)
Cured (rigid)	2 - 4 hours.....	4 - 8 hours

SANITARY PRECAUTIONS

Do not take internally. Avoid prolonged breathing of vapors. Work in a well-ventilated area. Avoid skin contact. Protective gloves should be worn. If contact occurs: wash skin with soap and water. Avoid eye contact. If contact occurs: rinse well with water for 15 minutes, contact physician.

TCC-205 Tech/Revised 1/30/15
Supersedes 6/19/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it	JAPAN +81 5 64 26 25 91 sales.japan@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	MIDDLE EAST +971 7 2432227 axsonmiddleeast@axson.com	SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	SPAIN +34 9 32 25 16 20 spain@axson.com	U.K. +44 16 38 66 00 62 sales.uk@axson.com	