

PRODUCT DATA SHEET

RIM 976

LOW PRESSURE RIM SYSTEM WITH A VERY HIGH TEMPERATURE RESISTANCE – SIMULATION OF PE / PP AND ABS

APPLICATIONS

- Manufacture of housings and coverings with high temperature resistance
- Manufacture of impact resistant technical parts, e.g. under-the-hood parts
- Stiff parts

MAIN PROPERTIES

- Simulation of PE / PP and ABS
- Very high temperature resistance with 150 °C
- Can be mixed with RIM 975 in order to reach different flexural modulus between 1,000 and 2,000 MPa

DESCRIPTION

Basis	Two component polyurethane system
Component A	RIM 976 , polyol, black
Component B	RIM 900 , MDI-based isocyanate, dark amber

PHYSICAL PROPERTIES

		Polyol (A)	Isocyanate (B)
Components		RIM 976	RIM 900
Viscosity, 25 °C	mPa.s	~ 1,500	~ 1,500
Density, 25 °C	g/cm ³	1.09	1.22
Mixing ratio A:B	in parts by weight	100	100
Mixing ratio A:B, 25 °C	in parts by volume	100	89
		Mixture	
Colour		black	
Pot life, 25 °C, 100 g	s	~ 35 – 40	
Demoulding time, 23 °C	min	~ 10	
Maximal casting thickness	mm	10	

MECHANICAL PROPERTIES

approx. values

Density, 23 °C	ISO 2781	g/cm ³	1.18
Shore hardness	ISO 868	-	D 80*
Flexural modulus	ISO 178	MPa	2,000*
Tensile strength	ISO 527	MPa	50*
Elongation at break	ISO 527	%	10*
Impact resistance	ISO 179	kJ/m ²	40*
Linear shrinkage, 23 °C			
- 2 to 3 mm thickness	Internal test	mm	5 – 6*
- 4 to 5 mm thickness			8 – 9*

THERMAL AND SPECIFIC PROPERTIES

approx. values

Using temperature		°C	-20 – 130*
Glass transition temperature	ISO 11359	°C	150*
Coefficient of thermal expansion, [0, 100] °C	ISO 11359	10 ⁻⁶ K ⁻¹	110*

* values after postcuring:
4 h / 80 °C + 2 h / 130 °C

PACKAGING UNITS

- | | |
|----------------------------------|-------|
| ■ Polyol (A), RIM 976 | 18 kg |
| ■ Isocyanate (B), RIM 900 | 18 kg |

PROCESSING DATA

- The material and processing temperature should be at least 18 – 25 °C, mould temperature at least 55 – 60 °C.
- Component A must be stirred thoroughly before use.
- For processing, a suitable two-component meter mix and dispense machine should be used.
- The machine should be conform to the reactivity of the material and the volume of the casted parts. A static-dynamic or dynamic mixing unit is recommended.
- The machine vessel for component A must have a mixing unit. Furthermore, a heating unit for the machine vessels of both components is recommended.
- Machine vessel for both components must be moisture tight, e.g. by installation of a silicagel filter.
- Recommended release agents are Sika® Liquid Wax-852 or Sika® Liquid Spray-872. For more information, see Product Data Sheets of the release agents.
- Pay attention to dry conditions and dry mould surfaces (moisture content of wood < 7 %) while processing.
- Increased mould temperatures are decreasing the demoulding time.
- Further postcuring of the demoulded part can improve the final mechanical properties.
- Depending on the geometry and weight of the part, it is recommended to use a conformer while postcuring.
- Before overpainting, the parts have to be grinded or sandblasted. A polyurethane paint is recommended.
- Adekit A 310 adhesive is particularly recommended for bonding this resin to itself or with different materials, such as thermoplastics, steel, etc.
- Before repairing or bonding surfaces, degrease the part with alcohol or acetone liquid soap.

STORAGE CONDITIONS

Shelf life	▪ Polyol (A), RIM 976	12 months
	▪ Isocyanate (B), RIM 900	12 months
Storage temperature	▪ Polyol (A), RIM 976	15 - 25 °C
	▪ Isocyanate (B), RIM 900	15 - 25 °C
Crystallization	▪ After prolonged storage at low temperature, crystallization of B component may occur.	
	▪ This is easily removed by warming up for a sufficient time to a maximum of 40 – 60 °C.	
	▪ Allow to cool to requested processing temperature before use.	
Opened packagings	▪ Containers must be closed tightly immediately after use to prevent moisture ingress.	
	▪ The residual material needs to be used up as soon as possible.	

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Contact

SIKA DEUTSCHLAND GMBH
Stuttgarter Straße 139
72574 Bad Urach - GERMANY
Phone: +49 7125 940 492
Fax: +49 7125 940 401
E-Mail: tooling@de.sika.com
Website: www.sikaadvancedresins.de

SIKA AUTOMOTIVE FRANCE S.A.S.
ZI des Béthunes - 15, Rue de l'Equerre
95310 Saint-Ouen-l'Aumône
CS 40444
95005 Cergy Pontoise Cedex - FRANCE
Phone: +33 1 34 40 34 60
Fax: +33 1 34 21 97 87
E-Mail: advanced.resins@fr.sika.com
Website: www.sikaadvancedresins.fr

AXSON TECHNOLOGIES SPAIN, S.L.
Ramon Turro 100,1°
08005 Barcelona - SPAIN
Phone: +34 93 225 16 20
Fax: +34 93 225 03 05
E-Mail: spain@axson.com
Website: www.sikaadvancedresins.es

AXSON ITALIA S.R.L.
Via Morandi 15
21047 Saronno (Va) - ITALY
Phone: +39 02 96 70 23 36
Fax: +39 02 96 70 23 69
E-Mail: axson@axson.it
Website: www.sikaadvancedresins.it

AXSON UK LTD
Unit 15 Studlands Park Ind. Estate
Newmarket Suffolk, CB8 7AU - UNITED KINGDOM
Phone: +44 1638 660 062
Fax: +44 1638 665 078
E-Mail: sales.uk@axson.com
Website: www.sikaadvancedresins.uk

SIKA AUTOMOTIVE SLOVAKIA S.R.O.
Tovarenska 49
953 01 Zlate Moravce - SLOVAKIA
Phone: +421 37 6422 526
Fax: +421 376 42 25 27
E-Mail: axson.sk@axson.com
Website: www.sikaadvancedresins.sk

SIKA ADVANCED RESINS US
31200 Stephenson Hwy, Madison Heights,
MI 48071 - USA
Phone: +1 248 588 2270
Fax: +1 248 588 5909
E-Mail: axsonmh@axson.com
Website: www.sikaadvancedresins.us

SIKA AUTOMOTIVE EATON RAPIDS, INC.
1611 Hulst Drive MI 48827 Eaton Rapids - USA
Phone: +1 517 663 81 91
Fax: +1 517 663 05 23
E-Mail: axsonmh@axson.com
Website: www.sikaadvancedresins.us

SIKA AUTOMOTIVE MEXICO S.A. DE C.V.
Ignacio Ramirez #20 Despacho 202 Col.
Tabacalera C.P. 06030 CDMX - MEXICO
Phone: +52 55 5264 49 22
Fax: +52 55 5264 49 16
E-Mail: marketing@axson.com.mx
Website: www.sikaadvancedresins.mx

SIKA AUTOMOTIVE SHANGHAI CO. LTD.
N°53 Tai Gu Road
Wai Gao Qiao
Free Trade Zone, Pudong
200131 Shanghai - CHINA
Phone: +86 21 58 68 30 37
Fax: +86 21 58 68 26 01
E-Mail: marketing.china@axson.com
Website: www.sikaaxson.cn

AXSON JAPAN KK
2-5-12 Onishi Okazaki Aichi
444-0871 - JAPAN
Phone: +81 564 26 2591
Fax: +81 564 26 2593
E-Mail: sales.japan@axson.com
Website: www.sikaadvancedresins.jp

AXSON INDIA PVT. LTD.
Office n°8, Building Symphony C - 3rd Floor
Range Hills Road
Bhosale Nagar
Pune 411 020 - INDIA
Phone: +91 20 25560 710
Fax: +91 20 25560 712
E-Mail: info.india@axson.com
Website: www.sikaadvancedresins.in