



EL-315 SERIES
use with
EL-315-IHL, EL-315-1
and EL-315-2 HARDENERS



www.axson-technologies.com
31200 Stephenson Hwy

800.344.7776
Madison Heights, MI 48071

axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

EL-315 Series is a premium high temperature epoxy laminating system developed to withstand extreme heat conditions in composite tooling applications such as autoclave; bonding jigs; oven cured processing or heat induction resin transfer molding. Test results show the physical and mechanical properties of the EL-315 series to be among the highest attainable in high temperature epoxy laminating systems. This advantage minimizes CTE differentials and stresses, resulting in a dimensionally stable and durable composite mold or part. EL-315 resin is available with a choice of three different hardeners to allow adequate construction and bagging time on large or small laminates.

HANDLING CHARACTERISTICS @ 77°F (25°C)

	<u>EL-315R/315-IHL</u>	<u>EL-315R/315-1</u>	<u>EL-315R/315-2</u>
Mix Ratio (parts-by-weight).....	100R/25H.....	100R/19H.....	100R/24H
Specify Gravity.....	1.18 g/cc.....	1.09 g/cc.....	1.14 g/cc
Mixed Viscosity.....	2,500-4,000 cps.....	2,000-3,000 cps.....	4,000-5,000 cps
Work Life.....	50-75 minutes.....	50-60 minutes.....	180-210 minutes
Demold Time.....	Refer To Recommended Post Cure Schedule		
Color.....	Clear Amber/Black.....	Clear Amber/Amber.....	Clear Amber/Amber
Shelf Life Resin (in original unopened container).....	2 years.....	2 years.....	2 years
Shelf Life Hardener (in original container).....	2 years.....	2 years.....	2 years

PHYSICAL PROPERTIES

Tensile Strength (ASTM D-3039.93).....	33,690psi (232MPa).....	62,630psi (432MPa).....	56,090psi (387MPa)
*Tensile Elongation (ASTM D-3039.93).....	1.8%.....	1.7%.....	not available
Tensile Modulus (ASTM D-3039.93).....	2,593,000psi.....	4,048,000psi.....	3,900,000psi
.....	(17,878MPa).....	(27,910MPa).....	(26,890MPa)
Flexural Strength (ASTM D-790.92).....	44,540psi (307MPa).....	90,480psi (624MPa).....	76,200psi (525MPa)
Flexural Modulus (ASTM D-790.92).....	2,296,000psi.....	4,642,000psi.....	3,504,000psi
.....	(15,830MPa).....	(32,005MPa).....	(24,159MPa)
*Coefficient of Thermal Expansion(TMA) (ppm/°F (°C)).....	11 (19)		
*Heat Deflection Temp @264 psi(ASTM D-648.82).....	320°F (161°C).....	306°F (152°C).....	389°F (198°C)
*Tg by DMA.....	331°F (166°C).....	305°F (152°C).....	450°F (232°C)
*Notched Izod Impact Strength (ASTM D-256.93a).....	4.5 in-lbs/in.....	6.47 in-lbs/in.....	4.5 in-lbs/in
*Shrinkage.....	0.0015 in/in.....	0.0015 in/in.....	0.0036 in/in
*Hardness.....	88 Shore D.....	90 Shore D.....	90 Shore D

(*) Denotes Physical Testing conducted on neat resin castings
All other testing conducted on 6 ply – 7500 Style E-Glass Laminates

PRELIMINARY CURE SCHEDULE

On Model Cure for 24 hours @ 77°F (25°C)
+ 6 hours 150°F (66°C)

You may attach support structure and de-mold tool after this schedule is completed.

POST CURE SCHEDULE

After completing the Preliminary Cure Schedule, complete the following:

- 1 hour @ 200 F (93°C)
- 1 hour @ 250 F (121°C)
- 1 hour @ 300 F (149°C)
- 3 hours @ 350 F (177°C)

Install thermocouples to monitor the mold temperature throughout the post cure process.

HEATING AND COOLING RATES DURING POST CURE

Always allow tools made with ADTECH high temp systems to gel at room temperature before subjecting them to post cure (24 hours is usually sufficient). This will prevent excessive exotherm and shrink stress from occurring. When oven curing laminated molds, always place the mold in a room temperature oven. Increase oven temperature at a rate of no more than 50°F (30°C) per hour. When heat cure is completed, turn off oven and allow molds to remain in the oven. Never remove mold from oven until mold temperature has been lowered to less than 100°F (38°C).

QUALIFICATIONS

EL-315R/EL-315IHL H: Boeing MMS-102 and M41-03-01 Code RHL and IHL
McDonnell Douglas C1-655, QPL Code L-3

EL-315 Series Tech/Revised 12/30/14
Supersedes 5/21/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com MIDDLE EAST +971 7 2432227 axsonmideast@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it SPAIN +34 9 32 25 16 20 spain@axson.com	JAPAN +81 5 64 26 25 91 sales.japan@axson.com U.K. +44 16 38 66 00 62 sales.uk@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
--	--	--	---	--	---	---