

PRODUCT DATA SHEET

SikaBiresin® RE 700-04 POLYOL/ SikaBiresin® RE 106 ISOCYANATE*

*(previously RE 11700-(04) / RE 1060)

ELECTRICAL POLYURETHANE RESIN FLEXIBLE – TRANSPARENT

DESCRIPTION

Clear Casting resin for LED and electronic components protection.

PROPERTIES

- Flexible
- Transparency
- Two-component liquid polyurethane
- Good UV resistance

PHYSICAL PROPERTIES

Composition			POLYOL	ISOCYANATE	MIXED
			SikaBiresin® RE 700-(04)	SikaBiresin® RE 106	
Mix ratio by weight			100	100	
Mix ratio by volume at 25 °C			100	87	
Aspect			liquid	liquid	Liquid
Colour			Transparent	Transparent	Transparent
Viscosity at 25 °C	(mPa.s)	ISO 2555 : 2018	70	1.200	200
Specific gravity at 25 °C	(g/cm³)	ISO 1675 : 1985	1,01	1,15	-
Specific gravity cured solid		ISO 2781 : 1996	-	-	1,13
Gel time at 25 °C (200 g)	(min)	Gel Timer TECAM			30

MECHANICAL PROPERTIES at 23 °C ⁽¹⁾

Hardness	ISO 868 : 2003	Shore A1	70
Tensile Strength		MPa	2,5
Elongation at break	ISO 37 : 2011	%	120

(1) Average values obtained on standard specimens / Hardening 16 hours at 80°C and 24 hours at 23°C

THERMAL AND SPECIFIC PROPERTIES ⁽¹⁾

Working temperature	-	°C	-40 to + 80
Thermal conductivity	EN 993-15	W/m.K	0,2
Glass transition temperature (T _g)	ISO 11359 : 1999	°C	6
Coefficient of thermal expansion (CTE) [+30 to +70]°C	ISO 11359 : 1999	10 ⁻⁶ K ⁻¹	265
Water absorption (23°C – 24 Hours)	ISO 62 : 1999	%	1,3
Transparency Index		%	80
Directive 2015/863/EU (ROHS) ⁽²⁾	-	-	Conform

(1) Average values obtained on standard specimens / Hardening 16 hours at 80°C and 24 hours at 23°C.

(2) European directive on the restriction of the use of certain hazardous substances electrical and electronic equipment.

DIELECTRIC AND INSULATING PROPERTIES at 23°C ⁽¹⁾

Dielectric strength (50 Hz - 1 mm)	CEI 60243-1 E2 : 1998	kV/mm	26
Dielectric constant ε (100 Hz) +25°C	CEI 60250 : 1969	-	9,1
Dissipation factor tan δ (100 Hz)	CEI 60250 : 1969	-	0,04
Volume resistivity (1.000 V)	CEI 60093 E2 : 1980	Ω.cm	2.10 ¹²

(1) Average values obtained on standard specimens / Hardening 16 hours at 80°C and 24 hours at 23°C

PROCESSING

- Heat both part at minimum 25°C in case of storage at lower temperature.
- Mix both part during 2 minutes with a metallic spatula
- Degas the mixing 2 minutes under vacuum (minimum 5 mbar)
- Cast in a mold without any trace of humidity (dry at minimum 6H at 50°C)
- Maximal casting thickness for optimal transparency : 10 mm
- For the first use , make an evaluation test on one specimen
- During the polymerization , temperature must be between 20 and 30°C with relative humidity below 60% at 20°C and 40% at 30°C
- In case of using a dispensing machine, contact our technical service.

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

Shelf life is 6 months for the POLYOL and 12 months for ISOCYANATE in a dry place and in their original unopened containers at a temperature between 15 to 25°C.

Any open can must be tightly closed under dry inert gas (dry air, nitrogen, etc...).

PACKAGING

Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.com

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets.

VALUE BASES

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT

SIKA DEUTSCHLAND GmbH
Stuttgarter Straße 139
72574 Bad Urach – GERMANY
Tel.: (+49) 7 125 940 492
Fax.: (+49) 7 125 940 401
E-mail: tooling@de.sika.com
Website: www.sikaadvancedresins.de

SIKA AUTOMOTIVE FRANCE S.A.S.
ZI des Béthunes - 15, Rue de l'Equerre
95310 Saint-Ouen-l'Aumône
CS 40444
95005 CERGY PONTOISE Cedex – FRANCE
Tel.: (+33) 1 344 034 60
Fax: (+33) 1 342 197 87
E-mail: advanced.resins@fr.sika.com
Website: www.sikaadvancedresins.fr

AXSON TECHNOLOGIES SPAIN, S.L.
Polígono Industrial Congost - Guardaagullés, 8
08520 LES FRANQUESES DEL VALLES – SPAIN
Tel.: (+34) 932 25 16 20
E-mail: spain@axson.com
Website: www.sikaadvancedresins.es

AXSON ITALIA S.R.L.
Via Morandi 15
21047 Saronno (Va) – ITALY
Tel.: (+39) 02 9670 2336
Fax: (+39) 02 9670 2369
E-mail: axson@axson.it
Website: www.sikaadvancedresins.it

AXSON UK Ltd
Unit 15 Studlands Park Ind. Estate
Newmarket Suffolk, CB8 7AU – UNITED KINGDOM
Tel.: (+44) 1638 660 062
Fax: (+44) 1638 665 078
E-mail: sales.uk@axson.com
Website: www.sikaadvancedresins.uk

SIKA AUTOMOTIVE SLOVAKIA s.r.o.
Tovarenska 49
95301 ZLATE MORAVCE – SLOVAKIA
Tel.: (+421) 376 422 526
Fax: (+421) 376 422 527
E-mail: axson.sk@axson.com
Web site: www.sikaadvancedresins.sk

SIKA ADVANCED RESINS US
30800 Stephenson Highway
Madison Heights, Michigan 48071 – USA
Tel.: (+1) 248 588-2270
Fax: (+1) 248 577-0810
E-mail: axsonmh@axson.com
Web site: www.sikaadvancedresins.us

SIKA AUTOMOTIVE MEXICO S.A. DE C.V.
Ignacio Ramírez #20
Despacho 202 Col. Tabacalera
C.P. 06030 CDMX – MEXICO
Tel.: (+52) 55 5264 4922
Fax: (+52) 55 5264 4916
E-mail: marketing@axson.com.mx
Website: www.sikaadvancedresins.mx

SIKA AUTOMOTIVE SHANGHAI CO. Ltd
N°53 Tai Gu Road
Wai Gao Qiao
Free Trade Zone, Pudong
200131 Shanghai – CHINA
Tél.: (+86) 21 5868 3037
Fax: (+86) 21 5868 2601
E-mail: marketing.china@axson.com
Website: www.sikaadvancedresins.cn

SIKA JAPAN Ltd
2-5-12 Onishi Okazaki Aichi
444-0871 – JAPAN
Tel.: (+81) 564 26 2591
Fax: (+81) 564 26 2593
E-mail: sales.japan@axson.com
Website: www.sikaadvancedresins.jp

AXSON INDIA Pvt. Ltd.
Office n°8, Building Symphony C - 3rd Floor
Range Hills Road
Bhosale Nagar
PUNE 411 020 – INDIA
Tel: (+ 91) 20 25 56 07 10
Fax: (+ 91) 20 25 56 07 12
E-mail: info.india@axson.com
Website: www.sikaadvancedresins.in