



Sika® Coating Aktivator

Agent to improve adhesion on coatings

Technical Product Data

Chemical base	Solvent-based adhesion promoter
Colour	Colourless to slightly yellow
Density (CQP ¹ 006-3 / ISO 2811-1)	0.7 kg/l approx.
Flash point (CQP 007-1 / ISO 13736)	-4°C (25°F)
Application temperature	5 - 40°C (40 - 105°F)
Application	Wipe-on, wipe-off with lint-free paper towel
Consumption	30 - 60 ml/m ² approx.
Flash-off time ³	above 15°C (60°F) 10 min below 15°C (60°F) 30 min maximum 24 hours
Storage	Store in sealed container in a cool dry place below 25°C (75°F)
Shelf life	12 months

¹⁾ CQP = Corporate Quality Procedure

²⁾ 23°C (73°F) / 50% r.h.

³⁾ In specific applications temperature and drying time may be different

Description

Sika® Coating Aktivator is a pre-treating and activating agent specifically formulated for the pre-treatment of painted and coated surfaces prior to the application of various Sika polyurethane adhesives.

Sika® Coating Aktivator is manufactured in accordance with ISO 9001 / 14001 quality assurance system and the responsible care program.

Areas of Application

Sika® Coating Aktivator is used to activate and improve adhesion to coil coated, powder coated, stove enamel and other painted or primed substrates.

Sika® Coating Aktivator can not be used on glass or ceramics for primer less bonding.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

Method of Application

Wipe bond faces with a clean lint-free paper towel moistened with Sika® Coating Aktivator. Apply Sika® Coating Aktivator sparingly, and once only. Immediately wipe-off any excess with a clean, dry lint-free paper towel.

Ideal application and surface temperature is between 15°C and 25°C (60°F to 75°F).

Consumption depends on the specific nature of the substrates and manufacturing process.

Tightly re-seal container immediately after each use.

Important Note

Sika® Coating Aktivator contains solvent, which may dull the surface finish of some freshly applied paints. Preliminary trials should be carried out. Do never apply Sika® Coating Aktivator to porous substrates.

Sika® Coating Aktivator must be used within one month of opening the can. After this time the product is to be discarded.

Prolonged exposure to atmospheric moisture will cause Sika® Coating Aktivator to become inactive.

Further Information

Working instructions issued for a defined application may further specify technical data contained in this Product Data Sheet. Copies of the following publications are available on request:

- Material Safety Data Sheet
- Sika Pre-treatment Chart

Packaging Information

Can	250 ml
	1 l
	5 l

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Further information available at:
www.sika.ch
www.sika.com

Sika Schweiz AG
Business Unit Industry
Tueffenwies 16
CH-8048 Zurich
Switzerland
Tel. +41 58 436 40 40
Fax +41 58 436 55 30

