

Thickening agent for Biresin[®] EP and PUR systems Stellmittel T - Extender T

Areas of Application

- For thickening of **Biresin[®]** PUR and EP systems (laminating and casting resins)

Product Benefits

- White powder
- High specific surface
- Excellent thickening effect in low additions

Description

- Basis fibrous, high disperse HD-polyethylene powder

Processing Data

Density	g/cm ³	0.96
Bulk density	g/l	~ 40

Packaging

Individual components **Stellmittel T - Extender T** 1.0 kg net

Processing

- The material and processing temperature must be 18 - 25°C.
- Stellmittel T is to be added to resin or hardener component as well as to the ready mixed components.
- For the application of Stellmittel T pay attention to the processing conditions of Biresin[®] resins too.

Storage

- Minimum shelf life is 12 month under room condition (18 - 25°C), when stored in original un-opened containers.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: tooling@de.sika.com

Internet: www.sika.com

